

PROPERTIES

<u>Physical Properties</u>	<u>Units</u>	<u>Test Method</u>
Thickness	0.15+/-0.05mm	ASTM D1000
Color	Dark Gray	Visual
Tensile Strength	750 PSI	ASTM D1000
Thermal Impedance	0.05C-in/W	ASTM C-177
Thermal Conductivity	>7.0W/m-k	ASTM C-177
Temperature	-55°C ~ 200°C	
Adhesion	10 oz/in	ASTM D1000
Specific Gravity	2.1 ~ 2.3	
Filler Material	Graphite	100% natural graphite
Sulfur Content	Non content	
Ash Content	Non content	
Moisture Content	<0.1%	

OUTLINE DRAWING

